

What is claimed is:

1. A solid titanium catalyst component being obtained by a process comprising:

5 a step of bringing (a) a liquid magnesium compound into contact with (b) a liquid titanium compound in the presence of (c) an organosilicon compound having no active hydrogen in an amount of 0.25 to 0.35 mol based on 1 mol of the magnesium compound (a); and

10 a step of elevating the temperature of the resulting contact product (i) to a temperature of 105 to 115 °C and maintaining the contact product (i) at this temperature,

15 said solid titanium catalyst component comprising magnesium, titanium, halogen and the organosilicon compound having no active hydrogen (c).

2. A solid titanium catalyst component being obtained by a process comprising:

20 a step of bringing (a) a liquid magnesium compound into contact with (b) a liquid titanium compound in the presence of (c) an organosilicon compound having no active hydrogen in an amount of 0.25 to 0.35 mol based on 1 mol of the magnesium compound (a); and

25 a step of elevating the temperature of the resulting contact product (i) to maintain the contact product (i) at a given temperature of 105 to 115 °C, wherein the organosilicon compound having no active hydrogen (c) is added in an amount of not more than 0.5 mol based on 1 mol of the magnesium compound (a) while the temperature of the

1002543-123601

5

*[Signature]*

1005548 1005548

15

4. / An ethylene polymerization process comprising polymerizing ethylene or copolymerizing ethylene and a comonomer in the presence of the catalyst as claimed in claim 3.